

natureplus e.V.

Award Guideline 0109

## **Jute Fibre Insulation**

Issued: June 2015

For the Awardance of the Eco-Label





# Award Guideline 0109

## Jute Fibre Insulation

Version: June 2015

## 1. Application Areas

The following criteria contain the requirements for the awardance of the natureplus eco-label for jute based insulation. The award guideline is to be applied exclusively to those products whose thermal insulation function is based upon the use of jute fibres. Mixtures with other fibres from renewable raw materials (e.g. hemp) are also eligible.

## 2. Award Criteria

The prerequisite for the awardance of the natureplus eco-label is the fulfilment of the basic criteria GL-0000 and of the chemicals directive GL-5001.

### 2.1 Suitability of Application

The manufacturer provides information about technical and physical characteristics of the product and specifies the standards, test procedures and methods used to determine these properties. If the applied standards contain requirements for the products, it is to be clearly indicated whether they are met.

The product meets the requirements for the suitability of application by holding the state-specific or the European technical approval.

The thermal nominal value at 10°C and  $u_{dry}$  as per EN ISO 10456 or a comparable standard must comply with the following requirements:

- Insulation not subject to pressure load (W, WL, WV)  $\lambda_{90,90} \leq 0,045 \text{ W/mK}$
- Insulation subject to pressure load (WD)  $\lambda_{90,90} \leq 0,065 \text{ W/mK}$
- Insulation functioning as plaster base (WD-PT)  $\lambda_{90,90} \leq 0,050 \text{ W/mK}$

The fire behaviour of the product must correspond at least to building material class E according to EN 13501-1.

In case the product is supplied to countries in which other requirements apply as the ones in the standards mentioned so far, these requirements must be met as well. The manufacturer states the countries where the product is distributed and provides official certification by approved testing institutions to confirm compliance with the requirements. The product must not, however, fall short of the requirements established by natureplus.



## **Award Guideline 0109**

### **Jute Fibre Insulation**

Version: June 2015

Page 3 of 10

The product must not be treated with compounds which prevent or strongly reduce its ability for water uptake or water release.

The product must be resistant to mould growth under the conditions of a professional installation. Evidence has to be provided in form of a rating of mould fungus growth as category 0 (no growth visible with microscopic analysis) according to EN ISO 846.

## **2.2 Composition, Forbidden Substances, Substance Restrictions**

At least 85% of the product based upon its dry weight must be made from renewable or mineral raw materials. Jute fibres as well as mixtures with other fibres from renewable raw materials (e.g. hemp) are permitted for use.

Only mineral additives are permitted as flame retardants. The proportion of flame retardants within the product may not exceed 15% of the dry weight of the product. The use of boron compounds as flame retardants or as protectant against microbial infestation is prohibited.

The use of synthetic support fibres is allowed up to a limit of 15% of the product dry weight. Chlorinated polymers are not permitted at all.

The application of biozides are not permitted.

The product is subject to laboratory analyses as laid down in section 3 and has to comply with the limit values stated therein.

## **2.3 Raw Material Sourcing, Production of Preliminary Products, Production**

By means of agreements with raw material suppliers and suitable receiving inspections, the manufacturer has to guarantee that the jute bags obtained for the fibre production were used for food transport and show no signs of mould growth. Proof of quality is to be presented.

If an additional fibre is used as a product component, the requirements for raw material sourcing of the corresponding natureplus guideline apply. Contamination with undeclared fibres of plant origin must not exceed 5%.

To ensure that the product is free of pesticide contaminations, the product is subject to analyses for pesticides as laid down in section 3 and has to comply with the limit values stated therein.

The manufacturer must demonstrate that a hazardous substance management according to national standards and regulations is available at the production facility for employee protection. Information on dust release and compliance with general dust limit values must be included therein. Where compliance with the general dust limit values or other occupational limit values cannot be guaranteed despite technical and organisational measures, personal protection



# Award Guideline 0109

## Jute Fibre Insulation

Version: June 2015

equipment must be available. It must be aimed for a minimisation of avoidable burdens of the employees.

## 2.4 Usage

The product must not exhibit any unpleasant or foreign smells or odours. The emissions during use have to be in compliance with the limit values according to section 3.

## 2.5 Recycling/Disposal

The product must be suitable for safe disposal in a waste incineration facility.

## 2.6 Ecological Parameters

The manufacturing of all products of this product group must be in compliance with the ecological parameters listed below. The determination of the ecological parameters includes the transport of the jute bags starting with their arrival at a European port and the recycling process. The manufacturing process of the jute bags in the country of origin is not part of the assessment.

	Guide values <sup>1</sup>
Ecological parameters per FU <sup>2</sup>	Apparent density <90kg/m <sup>3</sup>
Primary energy input of non renewable total resources (PENRE <sup>3</sup> ) [MJ]	50
Primary energy input of non renewable and renewable total resources (PET <sup>4</sup> ) [MJ]	90
Photochemical ozone creation potential (POCP) [kg ethylen-equiv.]	0,0015
Acidification potential (AP) [kg SO <sub>2</sub> -equiv.]	0,012
Eutrophication potential (EP) [kg PO <sub>4</sub> <sup>3-</sup> -equiv.]	0,007
Global-warming potential (GWP) [kg CO <sub>2</sub> equiv.]	3
Abiotic depletion potential (ADP) [kg Sb equiv.]	0,00003

If a single guide value is exceeded, it will be decided on a case by case basis whether this is permissible for the purpose of optimising the complete product manufacturing process.



# Award Guideline 0109

## Jute Fibre Insulation

Version: June 2015

<sup>1</sup>Testing method: Calculation of the ecological parameters according to natureplus® implementing provisions for life cycle assessments; inventory analysis analogous to ISO 14040ff; efficiency categories according to CML-IA version 4.1 from October 2012 and characterised as baseline; primary energy requirement according to Frischknecht 1996; global-warming potential 1994/100 years; system limits: raw material sourcing to products ready for shipment

<sup>2</sup> FU: Functional Unit, corresponds to a thermal resistance of 1 m<sup>2</sup>K/W.

<sup>3</sup> PENRE: **p**rimary **e**nergy input of **n**on renewable **e**nergy resources

<sup>4</sup> PET: **p**rimary **e**nergy inputs of renewable and non renewable **t**otal resources

## 2.7 Declaration

The product packaging should display a full declaration of the input materials listed, analogue to the EU-Cosmetic Regulations, according to the declining mass percentage. If it is not possible to display this information directly on the product packing, it should be provided with the product in a technical datasheet or sales leaflet (in English or in the national language). If intermediate/preliminary products or formulations are used as input substances and the proportion present in the final product is >0.1 M-%, then all the substances used within these must also be taken into account for the declaration.

For naming the input materials as part of the declaration the following applies:

- More than 1 M-% - designation of the substance in question
- Less than 1 M-% - at least a functional designation (e.g. "moth proofing agent")

Furthermore, it is obligatory to provide the following information in a suitable form to the consumer or user (eg. online):

- Instructions for use and safety precautions
- Indications for storage and disposal
- Batch numbers
- City/town and country of production
- Indication of geographical origin of the key input material

When employing components with a potential for environmental hazard, the manufacturer has to suitably indicate measures to be taken to ensure environmental protection during removal and demolition (i.e. controlled deconstruction).

Additionally, the following product-specific information must be made available to the consumer or user.



# Award Guideline 0109

## Jute Fibre Insulation

Version: June 2015

Page 6 of 10

- Labelling according to the guidelines of the European Community (Communauté Européenne, CE marking) or the respective general technical approval, including a scope specification
- Apparent density in  $\text{kg/m}^3$
- Thermal nominal value  $\lambda_D$  according to EN ISO 10456 or an equivalent standard
- Thermal design value  $\lambda_R$  according to EN ISO 10456 or an equivalent standard
- Type and field of application, i.e. as per DIN 4108, Austrian standard ÖNORM B 6000
- Euro class according to EN 13501-1

## 2.8 Processing

The manufacturer must demonstrate whether working procedures avoiding dust release are available for the processing of the product. If this is the case, these procedures are to be recommended and suitably presented within the processing guidelines. If compliance with the general dust limit values might not be guaranteed, wearing personal protection equipment must be recommended.

## 2.9 Packaging

The packaging used must be recyclable. The manufacturer must participate in a recycling system if there is one for the corresponding material.

Paper and cardboard packaging must be made from recycled paper. Alternatively, paper from sources as per GL-5002 is permitted.

Plastic packaging must be comprised from polyolefins. PET, polystyrene or polycarbonates are allowed exceptionally in reasonable cases. Packaging made from PVC is generally not permitted.

Packaging must not contain biocides.

The natureplus certification mark has to be printed on the packaging after the awardance of the product.

## 3. Laboratory Tests

The products are subject to laboratory analyses to test for harmful substances and undesirable ancillary ingredients. A representative sample is collected during the site inspection. If the sample collection can not be conducted by a natureplus examiner, an independent person designated by natureplus can collect the sample. For products with different sizes but the same composition, a single sample is sufficient.

### 3.1 VOC - TVOC

The product is subject to a test-chamber examination to survey the emissions of VOC, SVOC and other volatile compounds and to check compliance with the limit values. Measurements usually occur after 3 and 28 days. When low VOC emissions are to be expected, the emissions test can be terminated early, if a measurement 7 days after loading of the test chamber does not object to this. The test-chamber examination is performed according to the current version of the test method TM-01 VOC.

#### Emission measurement after 3 days

Test parameters	Limits	Unit
VOC (VOC, VVOC, SVOC) classified in:  Regulations (EC) No. 1272/2008: categories Carc. 1A und 1B, Muta 1A und 1B, Repr. 1A und 1B; TRGS 905: K1, K2, M1, M2, R1, R2; IARC groups 1 u. 2A; DFG MAK-list III1, III2	< 1	$\mu\text{g}/\text{m}^3$
Total volatile organic compounds (TVOC)	$\leq 3000$	$\mu\text{g}/\text{m}^3$

#### Emission measurement after 28 days

Test parameters	Limits	Unit
Total volatile organic compounds (TVOC)	$\leq 300$	$\mu\text{g}/\text{m}^3$
of which:		
Total bicyclic terpenes	$\leq 200$	$\mu\text{g}/\text{m}^3$
Total sensitising substances per MAK IV, BgVV-list cat. A, TRGS 907	$\leq 100$	$\mu\text{g}/\text{m}^3$
Total VOC (VOC, VVOC, SVOC) classified in:  Regulation (EC) No. 1272/2008: Kategorie Carc. 2, Muta 2, Repr. 2; TRGS 905: K3, M3, R3; IARC: group 2B; DFG MAK-list: III3	$\leq 50$	$\mu\text{g}/\text{m}^3$
Total aldehyde, C4-C11, acyclic, aliphatic	$\leq 100$	$\mu\text{g}/\text{m}^3$
Styrene	$\leq 10$	$\mu\text{g}/\text{m}^3$
Methylisothiazolinone (MIT)	< 1	$\mu\text{g}/\text{m}^3$
Benzaldehyde	$\leq 20$	$\mu\text{g}/\text{m}^3$
Total (VOC) without non-identified compounds	$\leq 100$	$\mu\text{g}/\text{m}^3$

A calculation of the r-value is performed. The limit value is  $\leq 1$ .

**Other emission measurements after 28 days**

Test parameters	Limit values	Unit
Total semi-volatile organic compounds (TSVOC)	$\leq 100$	$\mu\text{g}/\text{m}^3$
Formaldehyde	$\leq 36^{(1)}$	$\mu\text{g}/\text{m}^3$
Acetaldehyde	$\leq 36^{(1)}$	$\mu\text{g}/\text{m}^3$

<sup>(1)</sup>  $36 \mu\text{g}/\text{m}^3 \approx 0,03 \text{ ppm}$

**Termination criteria:**

The emissions test can be terminated 7 days after loading the test chamber, if the values measured at this time are lower than 50% of the 28-day threshold limits.

### 3.2 Element Analyses

The product is subject to an element analysis to determine the content of harmful elements and to check for undesirable contaminations. The measurements have to be in compliance with the limit values. The analysis is performed according to the current version of the test method TM-02 metals.

Element	Limit value	Unit
Arsenic (As)	2	mg/kg
Cadmium (Cd)	0,5	mg/kg
Cobalt (Co)	5	mg/kg
Chromium (Cr)	10	mg/kg
Copper (Cu)	50	mg/kg
Mercury (Hg)	0,2	mg/kg
Nickel (Ni)	10	mg/kg
Lead (Pb)	5	mg/kg
Antimony (Sb) <sup>(1)</sup>	2	mg/kg
Tin (Sn)	10	mg/kg
Thallium (Tl)	1	mg/kg
Zinc (Zn)	500	mg/kg



<sup>(1)</sup> As antimony acts as a catalyst in polyester production, the limit value for antimony does not apply for products containing supporting fibres on polyester basis.

### 3.3 Other Analyses

Test parameters	Limit values	Unit	Method
Halogenic organic compounds: AOX/EOX	≤ 1	mg/kg	TM-03 Halo
Odour	≤ 3	Odour intensity	TM-04 Odour
Total pesticides	≤ 1	mg/kg	TM-05 Pesticides
Individual pesticides  Organochlorine pesticides: Aldrin, Chlordane, DDD, DDE, DDT, Dichlofluanid, Dieldrin, Endrin, Heptachlor, Hexachlorobenzene, Lindane, Pentachlorophenol  Organophosphate pesticides: Dimethoat, Fenthion, Parathion-methyl, Parathion-ethyl, Phosalon  Pyrethroids: Cypermethrin, Lambda-Cyhalothrin, Permethrin  Other: Benomyl, Carbendazim, Prochloraz	≤ 0,5	mg/kg	TM-05 Pesticides

### Test Methods

**TM-01 VOC:** Volatile Organic Compounds VOC/TVOC, formaldehyde, acetaldehyde and TSVOC: DIN EN ISO 16000 series expanded by the natureplus implementation rules.

**TM-02 Metals:** ICP-MS measurements according to DIN EN ISO 17294-2, supplemented with the natureplus implementation rules and a sample preparation adjusted to the issue analysed.

**TM-03 Halo:** Halogenic organic compounds after combustion, determined by microcoulometry according to the natureplus implementation rules "AOX/EOX".

**TM-04 Odour:** natureplus implementation rules "odour intensity", 6-degree grading scale 24h after loading the test chamber



**Award Guideline 0109**  
**Jute Fibre Insulation**  
Version: June 2015

Page 10 of 10

**TM-05 Pesticides:** DFG S 19 supplemented with the natureplus implementation rules.